

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE MAY 2010		2. REPORT TYPE		3. DATES COVERED 00-00-2010 to 00-00-2010	
4. TITLE AND SUBTITLE Bi-anisotropy of optical metamagnetics studied with spectroscopic ellipsometry				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Air Force Research Laboratory, Wright Patterson AFB, OH, 45433				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES Proceedings of CLEO/QELS 2010, San Jose, CA, USA, May 16-21, 2010					
14. ABSTRACT Sub-wavelength gratings of paired Ag strips are measured and analyzed using spectroscopic ellipsometry, and show significant angular dependence of the electric and magnetic resonance properties, along with evidence of bi-anisotropy.					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 2	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Bi-anisotropy of optical metamagnetics studied with spectroscopic ellipsometry

Vladimir P. Drachev, Tom Tiwald[†], Josh Borneman, Shumin Xiao, Alexander V. Kildishev, Vladimir M. Shalaev, and Augustine Urbas[‡]

Birck Nanotechnology Center and School of Electrical and Computer Engineering, Purdue University, West Lafayette, IN 47907, USA

[†]*J.A. Woollam Co., Inc., Lincoln, NE 68508*

[‡]*Air Force Research Laboratory, WPAFB, OH 45433*

vdrachev@ecn.purdue.edu

Abstract: Sub-wavelength gratings of paired Ag strips are measured and analyzed using spectroscopic ellipsometry, and show significant angular dependence of the electric and magnetic resonance properties, along with evidence of bi-anisotropy.

©2010 Optical Society of America

OCIS codes: (160.3918) Metamaterials; (260.2130) Physical optics, ellipsometry and polarimetry;

Metamaterials can be considered in general as a bi-anisotropic material where the wave vector is related to not only permittivity and permeability but also to magneto-electric coupling coefficients. The constitutive relations for Maxwell's equations become more sophisticated in this case. They take the form [1]

$$\overline{D} = \overline{\varepsilon} \cdot \overline{E} + \overline{\xi} \cdot \overline{H}, \quad \overline{B} = \overline{\zeta} \cdot \overline{E} + \overline{\mu} \cdot \overline{H},$$

where \overline{D} depends on both \overline{E} and \overline{H} , and so does \overline{B} via the corresponding tensors. For the nonzero nondiagonal elements, $\xi_{xy} = -\xi_{yx} = \zeta_{xy} = -\zeta_{yx} = \frac{i}{c} \xi_0$, the bi-anisotropy parameter results in different effective impedances for light directed along the $+z$ and $-z$ directions $Z_{\pm} = \mu_y / \sqrt{n \pm \xi_0^2}$; $n = \sqrt{\varepsilon_x \mu_y - \xi_0^2}$. Some examples of bi-anisotropic metamaterials have been discussed earlier [2-4] mainly for metamaterials based on split ring resonators.

We study bi-anisotropic properties of metamagnetics based on subwavelength gratings consisting of pairs Ag strips [5]. All the demonstrated metamagnetics in the visible range so far were studied for a normal incidence of light. However the further development of metamaterials for imaging devices requires the accurate prediction and optimal design of material properties for arbitrary angles of light incidence [6]. We use a spectroscopic ellipsometry approach, which potentially enables the retrieval of all principal components of the optical tensors and brings an understanding of new effects and functionality associated with the oblique incidence of light at the interfaces of metamagnetics and negative index materials with usual optical materials.

Spectroscopic ellipsometry enables the measurement of angular and polarization dependences of the magnetic material. Metamaterial prototypes based on sub-wavelength gratings were fabricated by e-beam lithography similar to our previous experimental samples with a negative permeability in the visible range [5]. The negative permeability structure is a periodic array of pairs of silver strips 35x100nm separated by an alumina spacer of 40 nm in thickness. First, the geometry of the periodic thin silver strips is defined by use of an electron beam writer on a glass substrate initially coated with a 15-nm film of indium-tin-oxide (ITO). Then, electron beam evaporation is used to produce a stack of lamellar films. The period is about 250nm and the die size is about 500x500 μm . The transmission, reflection, and absorption spectra were measured and also modeled using finite-element method multiphysics (FEM) through commercially available Comsol Multiphysics software. Due to the semi-infinite nature of the strips, a 2D model was used. The transmission ellipsometry spectra at different angles (Fig.1) show that the resonance properties of the paired strips disappear for spectra at 40 and 60 degrees incidence, but is still present for 20 degrees. This is




Fig. 1. Transmission ellipsometry spectra of the magnetic grating at 0, 20, 40, and 60 degrees of the incident beam (plane of incidence perpendicular to the strips, p-polarization).

the qualitatively expected result since the projection of the electric field onto the sample plane is reduced as the angle of incidence increases. Strong angular dependence has been observed also for the reflection ellipsometry spectra. A significant difference in the ellipsometry spectra for parameters Psi and Delta were observed between front and rear illumination of the sample caused by the bi-anisotropy of the magnetic grating (Fig.2).




Fig. 2. Transmission ellipsometry spectra of the magnetic grating at the front and rear illumination and normal incidence of the beam (plane of incidence perpendicular to the strips, p-plane).

To summarize, a significant angular dependence of the metamagnetic resonance properties is observed with spectroscopic ellipsometry along with evidence of bi-anisotropy. All the experimental and simulated data, including generalized ellipsometry spectra and Mueller Matrix components and their analysis will be discussed in this talk.

This work was supported by the AFRL Materials & Manufacturing Directorate Applied Metamaterials Program.

References:

- [1] A. Serdyukov, I. Semchenko, S. Tretyakov, and A. Sihvola, "Electromagnetics of bi-anisotropic materials: theory and applications," Gordon and Breach Science Publishers 2001.
- [2] N. Katsarakis, T. Koschny, M. Kafesaki, E. N. Economou, and C. M. Soukoulis, "Electric coupling to the magnetic resonance of split ring resonators," *Appl. Phys. Lett.* **84**, 2943 (2004).
- [3] X. Chen, B.I. Wu, J. A. Kong, and T. M. Grzegorzczak, "Retrieval of the effective constitutive parameters of bianisotropic metamaterials," *Phys. Rev. E* **71**, 046610 (2005).
- [4] Z. Li, K. Aydin, and E. Ozbay, "Determination of the effective constitutive parameters of bianisotropic metamaterials from reflection and transmission coefficients," *Phys. Rev. E* **79**, 026610 (2009).
- [5] W. Cai, U. K. Chettiar, H.-K. Yuan, V. C. de Silva, A. V. Kildishev, V. P. Drachev, and V. M. Shalaev, "Metamagnetics with rainbow colors," *Opt. Express* **15**, 3333 (2007).
- [6] C. Menzel, C. Rockstuhl, T. Paul, T. Pertsch, and F. Lederer, "Retrieving effective parameters for metamaterials at oblique incidence," *Phys. Rev. B* **77**, 195328 (2008).